

M55J

HIGH MODULUS CARBON FIBER

M55J carbon fiber is an MJ-type high modulus fiber with enhanced tensile and compressive strength as compared to M series fibers. Manufactured in Japan.

PRODUCT DESIGNATION

M55J	B	6,000	5	0	B
Fiber Type	Twist*	Filament Count	Sizing Type	Surface Treatment	Sizing Amount

* B: Untwisted

FIBER PROPERTIES

PROPERTY	ENGLISH	METRIC	METHOD
Tensile Strength	583 ksi	4,020 MPa	TY-030B-01
Tensile Modulus	78.2 Msi	540 GPa	TY-030B-01
Strain at Failure		0.8%	TY-030B-01
Density		1.91 g/cm ³	TY-030B-02
Filament Diameter		5 μm	
Yield	6K	218 g/1000m	TY-030B-03

FUNCTIONAL PROPERTIES

PROPERTY	VALUE
CTE	-1.1 α · 10 ⁻⁶ /°C
Specific Heat	0.732 J/g · °C
Thermal Conductivity	1.556 J/(cm·s·°C)
Electric Resistivity	0.8 x 10 ⁻³ Ω·cm
Chemical Composition: Carbon	>99%
Na + K	<50 ppm

RESIN SYSTEM COMPATIBILITY

SIZING TYPE & AMOUNT	RESIN SYSTEM COMPATIBILITY	METHOD
50B (1.0%)	Epoxy, phenolic, polyester, vinyl ester	TY-030B-05

COMPOSITE PROPERTIES

PROPERTY	ENGLISH	METRIC	METHOD
Tensile Strength*	293 ksi	2,020 MPa	ASTM D-3039
Tensile Modulus*	49 Msi	338 GPa	ASTM D-3039
Tensile Strain		0.61%	ASTM D-3039
Compressive Strength*	129 ksi	890 MPa	SACMASRM1R-94
Flexural Strength*	171 ksi	1,180 MPa	ASTM D-790
Flexural Modulus*	40 Msi	274 GPa	ASTM D-790
ILSS	11 ksi	73.2 MPa	SACMASRM1R-94
In Plain Shear Strength	10 ksi	68 MPa	ASTM D-3518
90° Tensile Strength	5 ksi	37 MPa	ASTM D-3039

*Normalized to 60% fiber volume. Cured with #2500 epoxy at 130 °C.




PACKAGING

The table below summarizes the tow sizes, twists, sizing types, and packaging available for standard material. Other bobbin sizes may be available on a limited basis.

TOW SIZES	BOBBIN NET WEIGHT (kg)	BOBBIN TYPE	BOBBIN SIZE (mm)					SPOOL PER CASE	CASE NET WEIGHT (kg)
			a	b	c	d	e		
6K	0.5	II	76	82	192	107	156	24	12

Bobbin Type:



Please refer to SDS for handling and disposal.

For more information or purchasing inquiries:
sales@toraycma.com | www.toraycma.com | 253-846-1777

The data listed herein are lot averages and for reference purposes only. The results are not intended for specification purposes. These commodities, technology or software were exported from the United States in accordance with the Export Administration Regulations. Diversion contrary to U.S. law is prohibited.